

Più®Stretch - Corelles



Più® Stretch - LESS STRESS

The new generation of pre-stretched stretch film

PIÙ®Stretch.**PIÙSavings**

PIÙstretch reduces the amount of material required by as much as 50%.

PIÙLight

A reel of PIÙstretch weighs 70% less than a traditional 300 meters manual reel and ensures ease of application.

PIÙYield

The reel's width is not reduced during use and therefore a fewer wraps, per pallet, are required

PIÙOutput

Thanks to the lighter weight of the reel, the packaging of the pallets is easier and faster, resulting in significantly higher output.

PIÙStrength

Much improved wrapping tightness on the pallet than traditional film.

PIÙProtection

More protection for fragile products thanks to a more delicate application of the film on the pallet.

PIÙResistance

PIÙstretch can be used instead of any traditional stretch film thanks to the high quality of the raw materials used.

The film is much more resistant to tearing and impact.

PIÙEconomical

PIÙstretch eliminates all scrap caused by defective reels. The innovative production system ensures satisfactory use of all reels, even those accidentally damaged by impact or falling.

PIÙSafety

PIÙstretch improves and increases safety in terms of shipping because the pre-stretched film maintains a high force of cohesion to ensure the stability of the load on the pallet.

PIÙEnvironmental protection

The use of less film due to greater yield reduces the amount of waste.

PRE-STRETCHED MANUAL STRETCH FILM

<i>Properties</i>		<i>Units</i>	<i>Method</i>	<i>Value</i>		<i>Tol.</i>
THICKNESS		mm		0,008	0,010	
<i>Yield Stress</i>	L MD T TD	N	ASTM D 882	4,9 1,3	6,7 2,2	+/- 10%
<i>Tensile Strength</i>	L MD T TD	N	ASTM D 882	9 3,7	12,7 5,2	+/- 10%
<i>Ultimate Elongation</i>	L MD T TD	%	ASTM D 882	180 890	200 900	+/- 50
<i>Coefficient of friction</i>	STA DIN	-	ASTM D 1894			

Notice

The descriptions and figures contained herein are provided to customers by way of a general information for the purposes the product is intended for. These reflect Crocco's knowledge at the time of publication. Since the acknowledged various product applications by customers cannot be controlled by Crocco S.p.A, in no circumstances may Crocco S.p.A. be held responsible for the results obtained from the customers manufacturing processes or for the product used in combination with other substances. All data, information and suggestions here enclosed are to be considered just as an indication. The company will reserve the right to modify the data sheets without any notice.